



## UNDERBODY BRUSHABLE

EAN code: 5907588400343 item no.: 001032 con. 1kg

EAN code: 5907588400350 item no.: 001033 con. 2kg

EAN code: 5907588400367 item no.: 001034 con. 5kg



### PROPERTIES

This bitumen and rubber-based underbody preservative forms a flexible layer that perfectly protects the underbody of your car against stone chips, salt, water and mechanical damage. It is resistant to road salt and industrial fumes. It also acts as a sound absorber.



### COLOUR

● black



### METHOD OF USE

The underbody preservative can be easily applied with a brush. Thoroughly clean, degrease and then dry the conserved areas. After 24 hours the vehicle is fit for use.



### SURFACE

- **two-component acrylic primer** - apply varnish or control powder. After sanding, blow, degrease with "BOLL silicone remover" and then apply another coat.
- **epoxy primer** - can be used to isolate materials. After sanding, blow, degrease with "BOLL silicone remover" and then apply another coat.
- **polyester putties** - sand, blow and degrease with "BOLL Silicone remover" and then apply the next coat.



### INFORMATION

**Do not spray toward engine, transmission, brake parts or exhaust system. CAN NOT BE VARNISHED.**



## APPLICATION



Thoroughly clean and mat the surface



Thoroughly clean and degrease the surface




For corroded surfaces, we suggest using BOLL rust neutralizer or BOLL anticorrosive paint.



Mix thoroughly



Apply evenly with a brush



Recommended coating thickness 2-4 mm



Drying time: approx. 5-7 hours at temp. 20°C  
After 24 hours the vehicle is fit for use



## PHYSICAL PROPERTIES

density (at 20°C):

1,30 g/cm<sup>3</sup>



## EQUIPMENT CLEANING

Wash the brush with nitrocellulose solvent (Nitro) or white spirit.



## STORAGE CONDITIONS



Protect the product from excessive heat and cold. Avoid direct exposure to sunlight. Store in a dry place.



## SHELF LIFE

Two years from the production date on the packaging.



## SAFETY

See Safety Data Sheet.



## OTHER INFORMATION

All technical data are approximate values. We advise you to test the material to ensure suitability for your specific application. The producer reserves the right to improve the product and change the technical conditions with the possibility of making changes inside the specification.