

### TECHNICAL DATA SHEET RUST CONVERTOR

**EAN code:** 5907588408578 item no.: 00140194 cap. 60 ml  
**EAN code:** 5907588406093 item no.: 00140193 cap. 250 ml



#### + PROPERTIES

Product based on high-quality epoxy resins. Its unique composition provides the product with excellent priming and anticorrosive properties. It serves as both a primer and a base for subsequent layers, which can include various types of paints, varnishes, and polyester putties. It has a variety of applications, and can be applied directly to rust.

#### • COLOUR

 amber

#### ⤿ METHOD OF USE

Remove loose rust fragments, clean, degrease and then dry the surface to be covered. Pour off the necessary amount of the product into a separate container. Do not pour the residue into the original container. Can be painted with most paints and topcoats after 12 hours at 20°C. A test is recommended to check the compatibility of the product in a given application.

#### /// APPLICATION



Thoroughly clean and mat the surface



Thoroughly clean and degrease the Surface with "BOLL Silicon remover"



Mix thoroughly



Apply evenly to the rusted surface with a brush, roller or spray gun  
Depending on the degree of corrosion, it is recommended to apply 2 - 4 layers



Time between layers: 5 – 10 minutes



Can be painted with most paints and topcoats after 12 hours at 20°C



## PHYSICAL PROPERTIES

Viscosity:	min. 30 sek Ford 4
Dust dryness:	approx. 20 min at temp. 20°C
Density at 20°C:	0,930 g/cm <sup>3</sup>
Temperature of use:	+10°C – +25°C
Relative humidity:	45 – 60%



## STORAGE



Protect the product from excessive low and high temperatures. Avoid direct exposure to sunlight. Store in dry places.



## SHELF LIFE

Two years from the date placed on the package.



## SAFETY

See Safety Data Sheet.



## OTHER INFORMATION

All technical data are approximate values. We advise you to test the material to ensure its suitability for a specific application. The producer reserves the right to improve the product and change the technical conditions with the possibility of making changes inside the specifications.