



## SOFT LIGHT PUTTY



EAN code: 5907588411165 item no.: 002024  
content: putty 1 l + hardener 50g

### + PROPERTIES

Multifunctional low density polyester putty built on varied size synthetic fillers. Designed for professional paint work. Thanks to its construction, it is characterized by excellent application, smooth surface and excellent processing.

### • COLOUR

 blue

### = SURFACE

- **steel** - degrease, sand, blow and degrease again with "BOLL Silicone remover", then apply another coat.

---

- **aluminium** - degrease, sand, blow and degrease again with "BOLL Silicone remover", then apply another coat.

---

- **old paint coatings** - sand with P220-P280, blow, degrease with "BOLL Silicone remover", then apply the next coat.

---

- **two-component acrylic primer** - sand with P220-P280, blow, degrease with "BOLL silicone remover", then apply the next coat.

---

- **polyester laminates** - sand with P80-P120, blow and degrease with "BOLL Silicone remover", then apply another coat.

### ☰ INFORMATION

The putty should not be applied directly on wash primers or one-component acrylic and nitrocellulose products.



## APPLICATION



Thoroughly clean and mat the surface



Thoroughly clean and degrease the surface




Mixing ratio	by weight
putty	100 g
hardener	2-3 g

Stir thoroughly until uniform in color. Do not exceed the recommended amount of hardener. Mixture life: 4-6 minutes at 20°C



Apply with a spatula in several thin layers up to a total thickness of 3mm.



Drying time: 20-30 minutes at 20°C



IR illuminator: heat for 4 to 6 minutes. Do not exceed a temperature of 60°C.



**Preliminary grinding:** P80-P120  
**Finishing grinding:** P120-P240



Coverage:

- 2-component polyester putties
- 2-component polyester spray putties
- 2-component acrylic primers
- 2-component epoxy primers



## PHYSICAL PROPERTIES

density at 20°C:	1,30 g/cm <sup>3</sup>
solubility in water:	very slight
viscosity:	150 000 – 300 000 mPa*s
VOC content:	< 250 g/l (dopuszczalna: 250 g/l)



## EQUIPMENT CLEANING

Wash immediately after application with nitrocellulose thinner or thinner for acrylic products.



## STORAGE CONDITIONS



Protect the product from excessive heat and cold. Avoid direct exposure to sunlight. Store in a dry place.



## SHELF LIFE

24 months from the production date on the packaging.



## SAFETY

See Safety Data Sheet.



## OTHER INFORMATION

All technical data are approximate values. We advise you to test the material to ensure suitability for your specific application. The producer reserves the right to improve the product and change the technical conditions with the possibility of making changes inside the specification.